



DIVERSIFIED
TESTING LABORATORIES, INC.
 WORLDWIDE SERVICE

"We Test Per Your Request"

336 WEST FRONT STREET
 P.O. BOX 4004
 BURLINGTON, NORTH CAROLINA 27215
 PHONE (336) 227-7710 • FAX (336) 227-1175
www.diversifiedtestinglabs.com

December 1, 2015

Mr. John Horton
 SHINDIGZ
 One Party Place
 101 E. Carroll Road
 South Whitley, IN 46787

Reference: Laboratory Test Report
 Lab Identification No. 17660
 Invoice No. 48528 (Attached)

Dear Mr. Horton:

One (1) sample, identified as **POLY ETHYLENE SHEETING COLOR: DARK BLUE WATER - 100110724**, was received and tested in accordance with the National Fire Protection Association No. 701, "Standard Methods of Fire Tests for Flame Propagation of Textiles and Films, 2015 Edition, (Test 1, Small Scale)". The results are as follows:

<u>Specimen Number</u>	<u>Residual Flame</u> (seconds)	<u>Weight Loss</u> (percent)
1	0.0	5.66
2	0.0	1.76
3	0.0	1.41
4	0.0	1.63
5	0.0	2.43
6	0.0	2.36
7	0.0	2.29
8	0.0	1.32
9	0.0	3.05
10	0.0	<u>3.41</u>
AVG.	0.0	2.53

The sample submitted **meets** the minimum requirements of the above standard. The average percent weight loss cannot exceed 40% and the weight loss of individual specimens cannot exceed mean value plus three standard deviations. The average residual flame cannot exceed 2.0 seconds.

If there are any questions or when we can be of further assistance, please let us know.

Sincerely,

Bobby E. Puett

BEP/mr

OUR TEST REPORTS ARE FOR THE EXCLUSIVE USE OF THE CLIENT TO WHOM THEY ARE ADDRESSED. ANY COMMUNICATION TO OTHERS OR THE USE OF OUR COMPANY NAME MUST RECEIVE PRIOR APPROVAL. OUR TEST RESULTS APPLY ONLY TO THE SAMPLE TESTED AND ARE NOT NECESSARILY INDICATIVE OF THE QUALITIES OF APPARENTLY IDENTICAL OR SIMILAR PRODUCTS. SAMPLES NOT DESTROYED IN TESTING ARE RETAINED A MAXIMUM OF THIRTY DAYS. THE LETTERS, REPORTS OR NAME OF DIVERSIFIED TESTING LABORATORIES, INC. MAY NOT BE USED IN ADVERTISING TO THE GENERAL PUBLIC.